

General Performance Guidelines

The information shown on this page was determined under one set of test conditions and is supplied as a general guide only, as conditions vary with each application. Strength data given is for failure of the product or for sufficient deformation to make the product inoperable. No safety factor has been applied. It is recommended that the user test the product for his particular application.

No. 07 THERMOPLASTIC DRAW LATCH

PART No. 07-10-201-11 ; 07-10-201-12

MATERIAL : MEDIUM IMPACT
 COPOLYMER POLYPROPYLENE
 UL94 FLAMMABILITY RATING : HB

CYCLE TEST : TWO SAMPLES WERE TESTED (LATCHED
 AND UNLATCHED) UNTIL FAILURE.
 RESULTS : 350,000 AND 400,000 CYCLES